

## POLY-GLASS® MEGA-FAST LOW GLOSS RESIN

### EQUIPMENT, SUPPLIES AND TRAINING FOR THE **PROFESSIONAL REFINISHER**

NAPCO POLY-GLASSE MEGA-FAST LOW GLOSS RESIN

# Since 1979 NAPCO has been making bathtub refinishers happy.

We offer the highest quality refinishing coatings and equipment to get the job done right – the first time. Your ordering experience will be a breeze with our professional customer service.

You can rely on us for bath tub resurfacing expertise so you get the right product for your specific situation. Order your countertop and tub refinishing supplies and equipment online, 24/7. We offer the industries best hands-on bathtub, tile, sink and counter top reglazing training in convenient 3-day classes.

North American Polymer Company, LTD.

7315 Hamlin Avenue Skokie, IL 60076.3902 800.888.1081 **Use Poly-Glass Mega-Fast Low Gloss Resin on tubs, sinks, tile and vanities in both single tub homes and commercial accounts.** This low gloss resin minimizes dust contamination and will be dry to touch in 12 – 15 minutes. Wait 4 hours after application to use fixtures. Mega-Fast Resin will not crack or yellow over time and can last 10+ years when properly applied. Each gallon can cover approximately 16 tubs and is available in 22 standard colors plus custom colors as well. This item is compliant to California's 2020 VOC Regulations.

### **APPLICATION:** This is a 2 component Aliphatic Acrylic Polyurethane Resin. Mix 2 parts Mega-Fast Resin with 1 part

**Universal Catalyst.** For the average sized bathtub (or 35 square foot surface), mix 10 oz. of Mega-Fast Resin with 5 oz. of Universal Catalyst (by volume). Thin with 5 – 7 oz. of All Purpose Thinner. Spray 1 light tack coat followed by 2 wet coats. Pause between coats to inspect work. Allow the coating to tack before applying the next coat. At 75° F and 50% humidity, Poly-Glass Mega Fast will dry to touch in 12 – 15 minutes. Remove masking paper and apply caulking in 30 – 45 minutes after the last coat is applied.

#### **STORE INDOORS BETWEEN 50-90°F**

Shake constantly for 15 - 30 seconds before using.

© NAPCO Ltd. All Rights Reserved.